

AD-A096 067

LEHIGH UNIV BETHLEHEM PA MATERIALS RESEARCH CENTER F/G 11/9
A CORRELATION BETWEEN CRACK GROWTH RATE AND FRACTURE MODE TRANS--ETC(U)
JAN 81 P E BRETZ, R W HERTZBERG, J A MANSON N00014-77-C-0633

UNCLASSIFIED

TR-8

NL

[or]
GSA
Space



END
DATE
FILMED
4-81
DTIC

AD A U 96 067

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

LEVEL II

(12)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report #8	2. GOVT ACCESSION NO. AD-A096067	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) 6 Correlation Between Crack Growth Rate and Fracture Mode Transitions in Low-Density Polyethylene		5. TYPE OF REPORT & PERIOD COVERED 9 Interim Technical Report
7. AUTHOR(s) 10 P. E./Bretz, R. W./Hertzberg and J. A./Manson		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Materials Research Center Lehigh University Bethlehem, PA 18015		8. CONTRACT OR GRANT NUMBER(s) 15 N00014-77-C-0633
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research 14 TE-1 11 800 N. Quincy Street Arlington, VA 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR 356-670
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE 3 Jan 84
		13. NUMBER OF PAGES 5
		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) MAR 0 6 1981 E		
18. SUPPLEMENTARY NOTES Submitted to <u>Polymer</u>		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Fracture Polyethylene Fatigue Fractography Fatigue Crack Propagation		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Fatigue crack propagation rates in low-density polyethylene as a function of stress intensity factor were found to exhibit a discontinuity in the range $\Delta K = 0.4-0.6$ MPa/m. Within this range the FCP rate decreased with increasing ΔK . Fractographic examination revealed significant differences in the appearance of the fracture surfaces corresponding to values of ΔK below and above the transition range. While the reason for this behavior is not clear, the nucleation and growth of voids was involved throughout--the voids being smaller at low values of ΔK than at higher values.		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6601

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

408206

DRG FILE COPY

81 3 06 059

A Correlation Between Crack Growth Rate
and Fracture Mode Transitions in Low-Density Polyethylene

P. E. Bretz,¹ R. W. Hertzberg² and J. A. Manson²

The fatigue crack propagation (FCP) behavior of low-density polyethylene (LDPE) has been described by Andrews and Walker¹ and by Hertzberg, et al.² The results published by the former authors showed a discontinuity in the FCP behavior of this material at a crack growth rate of $\sim 10^{-3}$ mm/cycle; on the other hand, no such discontinuity in fatigue response was reported in the latter study. We have since re-examined the FCP behavior of compact-tension specimens of LDPE as a function of ΔK , over a wider range of ΔK (Fig. 1). These data show a decrease in crack growth rates (da/dN) with increasing ΔK between $\Delta K = 0.4 \text{ MPa}\sqrt{\text{m}}$ and $0.6 \text{ MPa}\sqrt{\text{m}}$, followed by an increase in da/dN with ΔK above $0.6 \text{ MPa}\sqrt{\text{m}}$; the solid lines shown in Figure 1 represent the data reported in reference 2. Thus the absence of any discontinuity in FCP behavior for LDPE reported in the earlier study² can be traced to the fact that the entire ΔK test range was above the transition range identified in the present investigation.

Since Andrews and Walker evaluated FCP rates as a function of \mathcal{T} , an elastic-plastic surface work parameter, while Hertzberg et al. measured crack growth rates as a function of the elastic stress intensity factor range, ΔK , these results cannot be compared directly. Nevertheless, it is interesting to note that the crack growth rate corresponding to the transition at A ($da/dN \sim 10^{-3}$ mm/cyc) agrees closely with the FCP rate at the discontinuity

¹Formerly Research Assistant, Lehigh University and currently Engineer, Alcoa Technical Center, Alcoa Center, PA 15069.

²Materials Research Center, Lehigh University, Bethlehem, PA 18015





Figure 1 Fatigue crack growth rates as a function of ΔK in LDPE. Note the decrease in da/dN with increasing ΔK between A and B. Solid lines represent FCP data for LDPE from reference 2.


reported by Andrews and Walker.¹ Thus, a phenomenological similarity is apparent between the LDPE data reported by Andrews and Walker and the present results which must reflect an equivalent intensity of the stress-strain field at the advancing crack tip.

An examination of the fracture morphology of LDPE revealed a marked change in the fracture surface appearance at the $da/dN-\Delta K$ transition at location B (Fig. 1). Below $\Delta K = 0.6 \text{ MPa}\sqrt{\text{m}}$, the fracture surface exhibited a tufted appearance consisting of small voids, while large voids dominated the fracture topography at higher ΔK levels (Figs. 2a and b). This contrast in appearance is very striking, considering the difference in magnification between Figures 2a and b ($\sim 700\times$ and $20\times$, respectively). It is believed that both of these fracture surfaces were produced by a void growth mechanism. Above $\Delta K = 0.6 \text{ MPa}\sqrt{\text{m}}$, though, there seems to have been a dramatic decrease in the nucleation rate of these voids and an enhanced opportunity for pronounced void growth. Curiously, these large voids appear to have been nucleated by local void clusters whose appearance was quite similar to the smaller voids seen at low ΔK levels (Fig. 2c). The discontinuity in FCP in FCP behavior reported by Andrews and Walker also was accompanied by a change in fracture morphology but was described differently, based on alternate microscopic techniques. Nevertheless, the phenomenological similarity of the two studies is confirmed. Unfortunately, while the correlation between crack growth rate behavior and fracture mode transition in LDPE is striking, the fundamental reason for this behavior remains unclear.

It is not clear why LDPE exhibits FCP discontinuities and high density polyethylene (HDPE) does not.³ In the latter study, fatigue crack growth rates increased continuously with increasing ΔK values for several molecu-



(a)



(b)



(c)

Figure 2 Void coalescence mechanism in LDPE: a) very fine voids at $\Delta K = 0.45 \text{ MPa}\sqrt{\text{m}}$, scale bar = $20 \text{ }\mu\text{m}$; b) coarse voids at $\Delta K = 1.0 \text{ MPa}\sqrt{\text{m}}$, scale bar = 0.5 mm ; c) center of coarse void showing texture similar to that shown in a), scale bar = $30 \text{ }\mu\text{m}$. Crack propagation direction from left to right.

lar weights and thermal histories. Additional complexities become apparent when comparisons are made with regard to fracture surface markings. For example, ultra-high-molecular-weight polyethylene⁴ and HDPE³ reveal various groupings of parallel fatigue fracture surface lines. Though White and Teh⁵ reported similar features in LDPE, none were identified in this investigation. Clearly, much additional research on the fatigue behavior of polyethylene is sorely needed.

Acknowledgements

This work was supported in part by the Office of Naval Research.

References

1. Andrews, E. H. and Walker, B. J., Proc. R. Soc. London A 1971, 325, 57.
2. Hertzberg, R. W., Nordberg, H. and Manson, J. A., J. Mater. Sci. 1970, 5, 521.
3. deCharentenay, F. X., Laghouati, F. and Deras, J. in "Deformation, Yield and Fracture of Polymers," Plastics and Rubber Institute, London 1979, p. 6.1.
4. Salvati, E. A., Wright, T. M., Burstein, A. H. and Jacobs, B., J. Bone and Joint Surgery 1979, 61-A, 1239.
5. White, J. R. and Teh, J. W., Polymer, 20, 1979, 764.

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Office of Naval Research Attn: Code 472 800 North Quincy Street Arlington, Virginia 22217	2	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 1211 Research Triangle Park, N.C. 27709	1
ONR Branch Office Attn: Dr. George Sandoz 536 S. Clark Street Chicago, Illinois 60605	1	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Area Office Attn: Scientific Dept. 715 Broadway New York, New York 10003	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
ONR Western Regional Office 1030 East Green Street Pasadena, California 91106	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
ONR Eastern/Central Regional Office Attn: Dr. L. H. Peebles Building 114, Section D 666 Summer Street Boston, Massachusetts 02210	1	Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
Director, Naval Research Laboratory Attn: Code 6100 Washington, D.C. 20390	1	Dr. A. L. Slafkosky Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
The Assistant Secretary of the Navy (RE&S) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1	Office of Naval Research Attn: Dr. Richard S. Miller 800 N. Quincy Street Arlington, Virginia 22217	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Naval Ocean Systems Center Attn: Dr. S. Yamamoto, Marine Sciences Division San Diego, California 91232	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1

TECHNICAL REPORT DISTRIBUTION LIST, GENNo.
Copies

Dr. Rudolph J. Marcus
Office of Naval Research
Scientific Liaison Group
American Embassy
APO San Francisco 96503

1

Mr. James Kelley
DTNSRDC Code 2803
Annapolis, Maryland 21402

1

TECHNICAL REPORT DISTRIBUTION LIST, 356A

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. Stephen H. Carr Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Picatinny Arsenal Attn: A. M. Anzalone, Building 3401 SMUPA-FR-M-D Dover, New Jersey 07801	1
Dr. M. Broadhurst Bulk Properties Section National Bureau of Standards U.S. Department of Commerce Washington, D.C. 20234	2	Dr. J. K. Gillham Department of Chemistry Princeton University Princeton, New Jersey 08540	1
Professor G. Whitesides Department of Chemistry Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Douglas Aircraft Co. Attn: Technical Library CL 290/36-84 AUTO-Sutton 3855 Lakewood Boulevard Long Beach, California 90846	1
Professor J. Wang Department of Chemistry University of Utah Salt Lake City, Utah 84112	1	Dr. E. Baer Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1
Dr. V. Stannett Department of Chemical Engineering North Carolina State University Raleigh, North Carolina 27607	1	Dr. K. D. Pae Department of Mechanics and Materials Science Rutgers University New Brunswick, New Jersey 08903	1
Dr. D. R. Chizman Department of Metallurgy and Material Science Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	NASA-Lewis Research Center Attn: Dr. T. T. Serofini, MS-49-1 21000 Brookpark Road Cleveland, Ohio 44135	1
Naval Surface Weapons Center Attn: Dr. J. M. Augl, Dr. B. Hartman White Oak Silver Spring, Maryland 20910	1	Dr. Charles H. Sherman Code TD 121 Naval Underwater Systems Center New London, Connecticut	1
Dr. G. Goodman Globe Union Incorporated 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1	Dr. William Risen Department of Chemistry Brown University Providence, Rhode Island 02192	1
Professor Hatsuo Ishida Department of Macromolecular Science Case-Western Reserve University Cleveland, Ohio 44106	1	Dr. Alan Gent Department of Physics University of Akron Akron, Ohio 44304	1

TECHNICAL REPORT DISTRIBUTION LIST, 356A

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Mr. Robert W. Jones Advanced Projects Manager Hughes Aircraft Company Mail Station D 132 Culver City, California 90230	1	Dr. T. J. Reinhart, Jr., Chief Composite and Fibrous Materials Branch Nonmetallic Materials Division Department of the Air Force Air Force Materials Laboratory (AFSC) Wright-Patterson AFB, Ohio 45433	1
Dr. C. Giori IIT Research Institute 10 West 35 Street Chicago, Illinois 60616	1	Dr. J. Lando Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1
Dr. M. Litt Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1	Dr. J. White Chemical and Metallurgical Engineering University of Tennessee Knoxville, Tennessee 37916	1
Dr. R. S. Roe Department of Materials Science and Metallurgical Engineering University of Cincinnati Cincinnati, Ohio 45221	1	Dr. J. A. Manson Materials Research Center Lehigh University Bethlehem, Pennsylvania 18015	1
Dr. Robert E. Cohen Chemical Engineering Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. R. F. Helmreich Contract RD&E Dow Chemical Co. Midland, Michigan 48640	1
Dr. T. P. Conlon, Jr., Code 3622 Sandia Laboratories Sandia Corporation Albuquerque, New Mexico	1	Dr. R. S. Porter Department of Polymer Science and Engineering University of Massachusetts Amherst, Massachusetts 01002	1
Dr. Martin Kaufmann, Head Materials Research Branch, Code 4542 Naval Weapons Center China Lake, California 93555	1	Professor Garth Wilkes Department of Chemical Engineering Virginia Polytechnic Institute and State University Blacksburg, Virginia 24061	1
Professor S. Senturia Department of Electrical Engineering Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. Kurt Baum Fluorochem Inc. 6233 North Irwindale Avenue Azusa, California 91702	1
		Professor C. S. Paik Sung Department of Materials Sciences and Engineering Room 8-109 Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1

DATE
FILMED
-8